



Maintenance Oil

Solvent-based, decorative oil for wooden decking & garden furniture




Colour	Availability			
	Quantity per pallet	672	200	96
	Packaging unit	3 x 0,75 l	2 x 2,5 l	1 x 5 l
	Type of container	Tin bucket	Tin bucket	Tin bucket
	Container code	01	03	05
	Art. no.			
douglas fir	2645	■	■	■
clear	2652	■	■	■
teak	2653	■	■	■
larch	2654	■	■	■
bangkirai	2655	■	■	■
special colours*	2656		■	■
*Minimum order 5 l				

Application rate

60 - 80 ml/m² per coat, depending on the absorption capacity of the wood



Range of use



- For use on interior and exterior wood
- Building elements with no or limited dimensional stability
- (Garden) furniture and wooden decking
- Wood types including teak, bangkirai, massaranduba, iroko, oak, larch & Douglas fir
- Thermally treated wood
- We recommend the use of WPC Impregnation Oil on WPC, bamboo and Resysta

Property profile



- Repels water
- Weatherproof and moisture-regulating
- Prevents wood from drying out
- Pigmented versions prevent greying



- Brilliant colours
- Easy to apply
- Subsequent treatment without sanding

Characteristic data of the product

Runout time s in ISO cup 3	>63.0 s
Binder	Linseed oil
Density (20 °C)	0.85 g/cm ³
Runout time s in DIN 4 cup	>17 s at 20 °C
Odour	Characteristic
Degree of gloss	Matt

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Certificates

- [Colour card](#)
- [DIN EN 71-3 "Migration of certain elements"](#)

Additional information

- [Applying oil-based products with a cloth](#)

Possible system products

- [Wood Preservative Primer* \(2066\)](#)
- [Wood Revitalizer \(2641\)](#)
- [Wood Cleaner \(2640\)](#)

*Use biocidal products carefully.
Always read the label and product information before use.

Preparation

- **Substrate requirements**
Wood building elements with limited or no dimensional stability: wood moisture content max. 18%
- **Substrate preparation**
Wood which is rich in active substances should be weathered for a few weeks or cleaned with Wood Cleaner before being treated for the first time in order to prevent delays in the drying process.
Use an agent such as Wood Cleaner to remove any dirt, grease and old coatings that could form a film, making sure not to leave any residue.
Clean any greyed wood surfaces with Wood Revitalizer.
Remove algae with Green Growth Remover*.
Pre-treat wood in outdoor areas which requires protection against rot and blue stain with Wood Protection Primer*.

Directions



- **Conditions for use**
Temperature of material, surroundings and substrate: from min. +5 °C to max. +30 °C.

Stir well.
Apply by brush.
Treat all sides (of decking) on the first coat if possible.
Apply the product using a varnish brush, a surface brush or a (cotton) cloth in the direction of the grain.
Take up any excess material with a dry brush or cloth after a maximum of 30 minutes.
Apply a second coat once the first has dried (approx. 12 hours).
Seal opened containers well and use contents as soon as possible.



Tips on use



Check colour, adhesion and compatibility with the substrate by setting up a trial area. Rainfall may cause water soluble substances to bleed from wood that is rich in such substances, e.g. oak, red cedar, afzelia, redwood, etc. This may lead to the discolouration of light-coloured masonry or render.

Clear does not protect from UV radiation (greying) and should therefore be used only on wood elements not directly exposed to weather (i.e. protected against direct sunlight, precipitation and wind). If a clear coating on a directly exposed surface outdoors is wished for, apply several coats and refresh at regular intervals.

Reapplications are required at least once a year in areas exposed to weathering. Although the various colours are matched to a specific type of wood, they can easily be used on other types of wood as well, in which case the look of the colour will differ from the corresponding sample.

Risk of spontaneous ignition (DGUV Information 209-046). Do not use in the same workplace as NC-based varnishes or stains. Collect contaminated textiles (e.g. cleaning cloths, work clothing, dust bags) in fireproof waste containers and dispose of in a fireproof manner (under water).

■ Drying

Dust-dry: approx. 4 hours

Can be coated: approx. 12 hours

Practice values at +20 °C and 65% relative humidity.

Low temperatures, poor ventilation and high humidity delay drying.

■ Thinning

Ready to use

Notes

On planed larch and softwoods with a high resin content, the coating may have reduced adhesion and resistance to weathering. This is especially the case on horizontal year rings, knots and areas of winter growth that are high in resin. Maintenance and renovation must be carried out more frequently on these surfaces. The only remedy for this is pre-weathering or very coarse sanding (P80). If these wood types are rough-sawn, considerably longer maintenance and renovation intervals are to be expected.

On terrace surfaces in the area of swimming pools, the increased exposure to chlorine, cleaning agents and intensive moisture can lead to reduced adhesion and weathering of the coating. Shorter maintenance and renovation intervals must be expected here.


Tools / Cleaning



Brush with natural bristles, flat brush, lint-free cotton cloth

Clean tools immediately after use with thinner and brush cleaner. Ensure that any residue from cleaning is disposed of correctly.

Storage / Shelf life



If stored unopened in its original container in a cool, dry place and protected against frost, the product will keep for at least 5 years.

Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal



Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Biocidal Products Regulation

*Use biocidal products carefully.
Always read the label and product information before use.

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (cat. A/f): 700 g/l (2010)
This product contains < 700 g/l VOC.

VOC	
Kat.	A/f
2010:	700g/l
max.:	700g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.